

Permeation times according to EN 374-3:2003

Article: 48

Code	Chemical	CAS	Minutes	Level
	Acetaldehyde, 99.5%	75-07-0	3	0
	Acetic Acid, 99%	64-19-7	223	4
B	Acetone, 99.5%	67-64-1	5	0
C	Acetonitrile, 99%	75-05-8	30	1
	Acrylic Acid, 99%	79-10-7	33	2
	Ammonium Fluoride, 40%	12125-01-8	>480	6
	Ammonium Hydroxide, 85%	1336-21-6	>480	6
	Amyl Acetate, 99%	628-63-7	193	4
	Amyl Alcohol, 99%	71-41-0	>480	6
	Aqua Regia	7647-01-0 and 7697-37-2	>480	6
	Bromopropionic Acid, Sat.		>480	6
	Butyl Acetat, 99%	123-86-4	72	3
	Butyl Cellosolve, 99%	111-76-2	>480	6
	Carbon Disulfide, 99%	75-15-0	14	1
	Carbon Tetrachloride, 99%	56-23-5	>480	6
	Cellosolve Acetate, 99%	111-15-9	175	4
	Citric Acid, 10%	77-92-9	>480	6
	Cyclohexanol, 99%	108-93-0	>480	6
	Diacetone Alcohol, 99%	123-42-2	333	5
	Dibutyl Phthalate, 99%	84-74-2	>480	6
G	Diethylamine, 99%	109-89-7	55	3
	Diisobutyl Ketone 80%	108-83-8	>480	6
	Dimethyl Sulfoxide, 99%	67-68-5	135	4
	Diocetyl Phthalate, 99%	117-81-7	>480	6
	Ethyl Ether, 99%	60-29-7	78	3
	Ethyl Glycol Ether, 99%		385	5
	Formaldehyde, 37%	50-00-0	>480	6
	Formic Acid, 95%	64-18-6	>480	6
	Furfural, 99%	98-01-1	43	2
	Gasoline 100%		>480	6
	Hexane, 99%	110-54-3	>480	6
	Hydrazine, 65%	302-01-2	>480	6
	Hydrochloric Acid, 38%	7647-01-0	>460	6
	Hydrofluoric Acid, 48%	7664-39-3	>480	6
	Hydrogen Peroxide, 30%	7722-84-1	>480	6
	Hydroquinone, Sat.	123-31-9	>480	6

	Isobutyl Alcohol, 99%	78-83-1	>480	6
	Isopropyl Alcohol, 70%	67-63-0	>480	6
A	Methyl Alcohol, 99%	67-56-1	199	4
	Methyl Butyl Ketone, 98%	108-10-1	36	1
	Methyl Cellosolve, 99%		210	4
	Methyl Ethyl Ketone, 99%	78-93-3	9	0
	Methylamine, 40%	74-89-5	>480	6
	Nitric Acid, 70%	7697-37-2	110	3
	Nitromethane, 99%	98-95-3	15	1
	Nitropropane, 99%	79-49-9	20	1
	Pentachlorophenol, 36%	87-86-5	>480	6
	Phenol, 90%	108-95-2	102	3
	Propyl Acetate, 99%	109-60-4	47	2
	Sulfuric Acid, 47%	7664-93-9	>480	6
	Tannic Acid, 37.5%	1401-55-4	>480	6
	Tetrachloroethylene, 99%	127-18-4	>419	5
F	Toluene, 99%	108-88-3	42	2
	Turpentine 100%	8006-84-2	>480	6
	Xylene 98%	1330-20-7	98	3