



Permeation times for glove TEGERA[®] 71000 according to EN 374-3:2003

Code	Chemical	CAS	Minutes	Performance level	NB
A	Methanol	67-56-1	19	1	Satra
J	n- Heptan	142-82-5	58	2	Satra
K	Sodium hydroxide, 40 %	1310-73-2	331	5	Satra
L	Sulphuric acid, 96%	7664-93-9	56	2	Satra

Notified Body 0321
SATRA Technology Centre
Wyndham Way, Telford way, Kettering
Northhamptonshire NN16 8SD
United Kingdom

Report: CHM 0239974/1545/EN, 9th of November 2015

Chemical products, permeation time based on literature:

Chemical	CAS	Minutes	Performance level
Solid EVA (ethylene-vinyl acetate)		480	6
Repex (Brand name)	Mixture	480	6
Colmodif (Brand name)	8050-28-0	480	6
Sasobit C 416 (Brand name)	8002-74-2	480	6
Calcium Chloride (solid)	10043-52-4	480	6
Zinc Stearate (solid)	557-05-1	480	6
Sulphur (solid)	7704-34-9	480	6