



## Permeation times for glove 848 according to EN 374-3

Code	Chemical	Formula	CAS	Minutes	Performance level
C	Acetonitril	C <sub>2</sub> H <sub>3</sub> N	75-05-8	< 5	0
	Ethanol	C <sub>2</sub> H <sub>5</sub> OH	64-17-5	8*	0
	Hexane	C <sub>6</sub> H <sub>14</sub>	110-54-3	10	1
	Hydrochloric acid, 37%	HCl	7647-01-0	42	2
	Hydrogen peroxide, 50%	H <sub>2</sub> O <sub>2</sub>	7722-84-1	6	0
	Isopropanol	(CH <sub>3</sub> ) <sub>2</sub> CHOH	67-63-5	50	2
A	Methanol	CH <sub>3</sub> OH	67-51-1	< 5	0
J	n- Heptan	C <sub>7</sub> H <sub>16</sub>	142-82-5	22	1
K	Sodium hydroxide, 40 %	NaOH	1310-73-2	480	6
	Sulfuric acid, 50 %	H <sub>2</sub> SO <sub>4</sub>	7664-93-9	480	6
L	Sulfuric acid, 96 %	H <sub>2</sub> SO <sub>4</sub>	7664-93-9	6	0
F	Toluene	C <sub>7</sub> H <sub>8</sub>	108-88-3	< 5	0

Issued by:  
Notified Body 0493  
CENTEXBEL GENT  
Technologiepark 7  
BE-9052 Zwijnaarde (Gent)  
Belgium

Reports: 56497/B (25.04.2007), 56497/D (05.06.2007), \*tested several times, 8 min is the shortest time, report 13.03013.01 (05.07.2013).

Code	Chemical	Formula	CAS	Minutes	Perf. level
	Cyclohexane	C <sub>6</sub> H <sub>12</sub>	110-82-4	60	3

Issued by Notified Body 0197  
TUV Reinland Product Safety GmbH  
Am Grauen Stein  
D-51105 Köln

Report 21102743 002 (23.06.2003)